

# RESURFACER



RESURFACER Water Based Acrylic. With elastic properties for high adhesion and flexibility. RESURFACER can bridge craze cracks on painted Plaster, it will also bond movement between two substrates.

- RESURFACER is applied onto painted or sealed surfaces.
- RESURFACER is also a flexible sealer for timber and roof coatings.

RESURFACER BONDS PAINTS TO PAINTED, CRACKED INTERNAL AND EXTERNAL WALLS.

Apply one coat of RESURFACER at 8m<sup>2</sup>/ litre if the cracks are fine and small in number. Apply two coats if the cracks are of medium to high density in number.

Allow each coat of RESURFACER to dry for at least 4 hours at 25C. Add 20% RESURFACER to paint, then mix and apply as normal.

RESURFACER can be used on Colorbond, Galvanized Iron and any painted steel.

Clean the old painted surface with a high-pressure cleaner. Allow the surface to dry. Remove any old flaky paint. Apply a coat of RESURFACER onto the old painted surface at the rate of 8-10m<sup>2</sup>/ litre. Allow RESURFACER to dry for at least 4 hours at 25°C before applying Paint e.g. VELVET, LOWSHEEN, SOLARBOND or SOLARFLEX.

RESURFACER CAN APPLY RENDERS TO WELL-BONDED, PAINTED WALLS:

High pressure water clean walls to remove any loose paint. Apply a coat of RESURFACER at 6-8m<sup>2</sup>/ litre per coat.

Allow RESURFACER to dry over night, Then apply a coat of RESURFACER while RESURFACER is wet, trowel on the render with CEMBOND added to the render mix at 2 Litres per 20kg of cement. The render will take longer to set.

RESURFACER FOR TIMBER OR CHIPBOARD: Apply one coat of RESURFACER at 6-8m<sup>2</sup>/ litre. Allow RESURFACER to dry for at least 4 hours at 25C before applying top coats for timber.

RESURFACER should be stored in a covered, cool area. The lid should be replaced after use or after a quantity has been decanted from it.

Clean tools with water immediately after use.

RESURFACER is sold in packs of 10Lt and 20 Litres.

RESURFACER is not a hazardous good as defined by Work-Safe Australia.

If walls have NOT been painted, a sealer must be applied prior to RESURFACER application.

Surfaces that are chalky, powdery or friable are not recommended for RESURFACER application unless sealed beforehand.

PAINT FACTORY  
U1 14 FIELDS STREET  
PINJARRA WA 6208  
AUSTRALIA

TELEPHONE  
TEL. (08) 9531 1184  
FAX. (08) 9531 1362  
MOB. 0419 931 064

PAGE 1

